

**AMENDMENTS TO THE CLAIMS**

This listing of claims will replace all prior versions, and listings, of claims in the application:

1. (original) A rotogravure coated paper comprising a coating layer containing a pigment and an adhesive on a base paper, wherein the coating layer contains an inorganic pigment having a volume-based distribution in which 65% or more of particles are in the particle diameter range of 0.4-4.2  $\mu\text{m}$  and a hollow sphere synthetic pigment having a mean particle diameter of 0.1-0.6  $\mu\text{m}$ .

2. (original) The rotogravure coated paper of claim 1 characterized in that the hollow sphere synthetic pigment is contained in an amount of 2-30 parts by weight per 100 parts by weight of the inorganic pigment.

3. (currently amended) The rotogravure coated paper of claim 1-~~or 2~~ characterized in that 3-12% by weight of an amorphous silicate is contained on the basis of the weight of the base paper.

4. (currently amended) The rotogravure coated paper of ~~any one of claims 1 to 3~~ claim 1 characterized in that 75 parts by weight or more of kaolin is included as an inorganic pigment component in 100 parts by weight of the inorganic pigment.

5. (currently amended) A process for preparing the rotogravure coated paper of ~~any one of claims 1 to 4~~ claim 1.